



Test Item	Test Method	Unit	Value	Typical Value
				SF490 503520SR
Peel Strength (90°)	IPC-TM-650, No.2.4.9	N/mm		0.82
Visible Light Transmittance	Shengyi Method	%		90.2
Dimensional Stability	Shengyi Method	%	1	1
Chemical Resistance	IPC-TM-650, No.2.3.2	%		90
Volume Resistivity	IPC-TM-650, No.2.5.17	-cm		1.5×10^8
Surface Resistance	IPC-TM-650, No.2.5.17			4.1×10^5



Adhesive Thickness: 20 - 20
 Copper Foil Thickness: 35 - 3
 PET Film Thickness: 75 188

Shengyi transparent PET-FCCL Designation

+2/-0
 supplied in rolls and standard width of 2/-0 . Other sizes could be available upon request.

Store in the room of dryness and no corrosive gases. One year when stored in the original packaging at room temperature. The products do not require refrigeration and should not be frozen.